

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 29.5 mm
 - Effective Area (A_e): 9.3mm²
 - Effective Area (A_{Min}): 9.3mm²
 - Effective Volume (V_e): 274mm³
- Approximate weight : 1.2g/pc**




T1303 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	Ordering code
CF196	2000 ±20%	800+30%/-20%	CF196T1303
CF139	2100 ±20%	825+30%/-20%	CF139T1303
CF130	3000 ±20%	1200+30%/-20%	CF130T1303
CF195A	5000 ±20%	1950+30%/-20%	CF195AT1303
CF265	5000 ±20%	1950+30%/-20%	CF265T1303
CF190	6000 ±20%	2350+30%/-20%	CF190T1303
CF197	7000 ±20%	2700+30%/-20%	CF197T1303
CF199	9000 ±20%	3500 ±30%	CF199T1303

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	13.0	13.4	12.6
B	7.0	7.3	6.7
C	3.2	3.4	3.0



For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf