

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.
Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 213.8mm
 - Effective Area (A_e): 226.1mm²
 - Effective Area (A_{Min}): 226.1mm²
 - Effective Volume (V_e): 48320mm³
- Approximate weight : 240.0g/pc**




T8714 OL (Un-coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	Ordering code
CF196	2000 ±20%	2650 +30%/-20%	CF196T8714
CF139	2100 ±20%	2800 +30%/-20%	CF139T8714
CF130	3000 ±20%	4000 +30%/-20%	CF130T8714
CF195A	5000 ±20%	6600 +30%/-20%	CF195AT8714
CF265	5000 ±20%	6600 +30%/-20%	CF265T8714
CF190	6000 ±20%	7900 +30%/-20%	CF190T8714
CF197	7000 ±20%	9300 +30%/-20%	CF197T8714
CF199	9000 ±20%	11300 ±30%	CF199T8714

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	87.4	88.75	86.05
B	54.0	55.0	53.0
C	13.8	14.25	13.35



For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf