


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 44.9mm
- Effective Area (A_e): 65.22mm²
- Effective Area (A_{Min}): 64.8mm²
- Effective Volume (V_e): 2928mm³


Approximate weight (without Gap): 14.5g/Set



EE2011S Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF196	2000 \pm 20%	2900 +30%/-20%	$\leq 0.40(200mT,16kHz,100^\circ C)$	CF196 EE2011S OL
CF139	2100 \pm 20%	3100 +30%/-20%	$\leq 0.29(100mT,100kHz,100^\circ C)$	CF139 EE2011S OL
CF297	2300 \pm 20%	3300 +30%/-20%	$\leq 0.26(100mT,100kHz,100^\circ C)$	CF297 EE2011S OL
CF130	3000 \pm 20%	4100 +30%/-20%	$\leq 0.44(200mT,16kHz,100^\circ C)$	CF130 EE2011S OL
CF195	5000 \pm 20%	5850 +30%/-20%	-	CF195 EE2011S OL
CF197	7000 \pm 20%	7150+30%/-20%	-	CF197 EE2011S OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value

For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf