


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 80.7mm
- Effective Area (A_e): 100mm²
- Effective Area (A_{Min}): 100mm²
- Effective Volume (V_e): 8071mm³


Approximate weight (without Gap): 36.0g/Set



EE3510 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF196	2000 \pm 20%	2650 +30%/-20%	$\leq 1.11(200mT,16kHz,100^\circ C)$	CF196 EE3510 OL
CF139	2100 \pm 20%	2800 +30%/-20%	$\leq 0.81(100mT,100kHz,100^\circ C)$	CF139 EE3510 OL
CF297	2300 \pm 20%	3050 +30%/-20%	$\leq 0.73(100mT,100kHz,100^\circ C)$	CF297 EE3510 OL
CF130	3000 \pm 20%	3700 +30%/-20%	$\leq 1.21(200mT,16kHz,100^\circ C)$	CF130 EE3510 OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value

For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf